

Material data sheet

Insulating strips of PA 66 GF25,
dry impact resistant

PA 66 GF25, dry impact resistant

Characteristic	Reference standard	Unit	Samples from extruded insulating strips		Samples from injection molding
			Dry ⁽¹⁾	Equilibrium moisture content ⁽²⁾	Dry ⁽¹⁾
Melting temperature	EN ISO 11357-3	°C	≥ 250 ⁽³⁾	≥ 250 ⁽³⁾	≥ 250 ⁽³⁾
Density	EN ISO 1183-1 or -3	g/cm ³	1.3 +/- 0.05	1.3 +/- 0.05	1.3 +/- 0.05
Annealing residue (glass fibre content)	EN ISO 1172	%	25 +/- 2.5	25 +/- 2.5	25 +/- 2.5
Tensile strength	EN ISO 527-2	N/mm ²	≥ 80 ⁽⁴⁾	≥ 50 ⁽⁴⁾	≥ 110 ⁽⁵⁾
Young's modulus	EN ISO 527-2	N/mm ²	≥ 4500 ⁽⁴⁾	≥ 2000 ⁽⁴⁾	≥ 6000 ⁽⁵⁾
Elongation at break	EN ISO 527-2	%	≥ 3 ⁽⁴⁾	≥ 7 ⁽⁴⁾	≥ 3 ⁽⁵⁾
Thermal conductivity	EN 12664	W/mK		0.30 ⁽⁶⁾	
Reaction to fire	EN 13501-1	-		class E ⁽⁷⁾	

TBGroup-Do-TPI-14_V8_07.2026

Material is suitable to be used as thermal barrier with mechanical functions according to EN 14024⁽⁸⁾

- 1) Sample water content less than 0.2 % by weight
- 2) Fast conditioning acc. to EN ISO 1110
- 3) Maximum temperature 300 °C
- 4) Specimen Type A22 - mean value with minimum sample size of 5 specimens at room temperature - tension measured in extrusion direction
- 5) Specimen Type A1
- 6) The declared value is taken from ISO 10077-2 and can be used for thermal performance of frames according to the mentioned standard
- 7) Report 24-003934-PR02
- 8) EN14024:2023 chapter 5.2 Report 24-003816-PR06 ift Rosenheim GmbH

In case of specific questions we gladly offer you our individual support

**Insulation solutions for
windows, doors, and facades**